



CITAL

PIETRA



GRAND LADO / HAND BOSSED

FEATURES

ORIGIN Europe

STONE Arenit Lithical Limestone

CHARACTERISTICS Dark gray background, extremely uniform in color and palette. Minimal variations with subtle white veining on occasion.

SIZE 3/8" (1cm), 1/2" (1.2cm), 3/4" (2cm), 1 1/4" (3cm)

RECOMMENDED USES Interior/exterior walls, interior/exterior floors, heavy traffic areas, fireplaces, columns, mouldings, etc.

POSSIBLE FINISHES Honed, Polished, Brushed, Sandblasted, Sandblasted+Brushed, Flamed, Flamed+Brushed, Bush Hammered.

Finishes are specific to each marble/stone type. Please inquire for finishes available.

CUSTOM SIZES MADE TO ORDER

TECHNICAL INFORMATION

Apparent Density	2.685 Kg/m ³	NF EN 1936
Water Absorption	0.20%	NF EN 1936
Open Porosity	0.35%	NF EN 1936
Capilarity	132 g/ m ³	NF EN 1925
Hardness Mohs	5.5 to 6 Mohs	NF EN 101
Compressive Strength	average 149.4 Mpa	NF EN 1926
Bending Strength	average 23.7 Mpa	NF EN 12372
Frost Resistance	144 cycles	NF EN 12371
Abrasion Resistance	20 mm	NF EN 14157