



CITAL

PIETRA



ONETTA / BUSH-HAMMERED

FEATURES

ORIGIN Europe

STONE Sedimentary Limestone

CHARACTERISTICS Brown, bronze, and cream fine grain background, with salt and pepper-like texture showing dark browns, blacks and light cream tones.

SIZE 3/8" (1cm), 1/2" (1.2cm), 3/4" (2cm), 1 1/4" (3cm)

RECOMMENDED USES High traffic internal/external flooring, internal/external walls, fireplace, column, moulding

POSSIBLE FINISHES Honed, Polished, Brushed, Sandblasted, Sandblasted+Brushed, Flamed, Flamed+Brushed, Bush Hammered.

Finishes are specific to each marble/stone type. Please inquire for finishes available.

CUSTOM SIZES MADE TO ORDER

TECHNICAL INFORMATION

Apparent Density	2690 Kg/m ³	EN 1936
Water Absorption	0.30%	EN 13755
Compressive Strength	average 135 Mpa	EN 1926
Bending Strength	average 15.6 Mpa	EN 12372
Abrasion Resistance	18.5 mm	EN 14157
Frost Resistance	125 cycles	ASTM C666